Printing date 07.09.2018

Version number 6

KARCHER

Revision: 04.09.2018

| 1.1 | Product identifier |
|---------------------------------|---|
| 1.2 No | de name: <u>RM 821</u> Relevant identified uses of the substance or mixture and uses advised against further relevant information available. Dication of the substance / the mixture Drying aid for vehicle washing plants |
| | Details of the supplier of the safety data sheet nufacturer/Supplier: |
| Alfı | red Kärcher SE & Co. KG red-Kärcher-Str. 28-40 71364 Winnenden |
| | tfach 160 71349 Winnenden |
| | : +49-7195-14-0 c : +49-7195-14-2212 |
| wwi | w.karcher.com |
| Kär Kär Bro Ban Oxo | tributor: rcher (UK) Ltd. rcher House wokhill Way abury on OX16 3ED eat Britain |
| | :: +44-1295-752-000 c: +44-1295-752-103 |
| Dep Tel. Fax safe | ther information obtainable from: partment PCD-D : +49-7195-14-2548 c : +49-7195-14-3164 etydata@karcher.com Emergency telephone number: |
| Spil Cal Wit | Hazardous Materials [or Dangerous Goods] Incidents II, Leak, Fire, Exposure, or Accident II CHEMTREC Day or Night hin USA and Canada: 1-800-424-9300 tside USA and Canada: +1 703-741-5970 (collect calls accepted) |



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

(Contd. of page 1)

| natic life with long lasting effects. No 1272/2008 Fording to the CLP regulation. Esting effects. accordance with local/regional/national/internatio |
|---|
| ording to the CLP regulation. sting effects. |
| ording to the CLP regulation. |
| sting effects. |
| |
| |
| |
| |
| accordance with local/regional/national/internation |
| accordance with local/regional/national/internation |
| accordance with local/regional/national/internation |
| |
| |
| |
| oduce an allergic reaction. |
| |
| anic halogen compounds (AOX), nitrates, heavy m |
| |
| |
| |
| |
| |
| |

| CAS: 94095-35-9 | fatty acids, (C10-C20 and C16-C18-unsat.), | 1-5% |
|--------------------------------|--|-----------------|
| EC number: 302-242-5 | reaction products with triethanolamine, di- ME | |
| Reg.nr.: 01-211947230933 | sulfate- quaternized TEA esterquat | |
| | 🚸 Flam. Liq. 3, H226; 🗘 Skin Irrit. 2, H315; | |
| | Eye Irrit. 2, H319 | |
| CAS: 541-02-6 | decamethylcyclopentasiloxane | 1-5% |
| EINECS: 208-764-9 | non-classified vPvB substance | |
| Reg.nr.: 01-2119511367-43-0000 | | |
| | | (Contd. on page |



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

| CAS: 5131-66-8 | propylene glycol monobutyl ether | 1-5% |
|---|---|------------|
| EINECS: 225-878-4 Index number: 603-052-00-8 Reg.nr.: 01-2119475527-28-XXXX | () Skin Irrit. 2, H315; Eye Irrit. 2, H319 | |
| CAS: 67-63-0 | propan-2-ol | 1-5% |
| EINECS: 200-661-7 Index number: 603-117-00-0 Reg.nr.: 01-2119457558-25-xxxx | | |
| CAS: 5989-27-5 | (R)-p-mentha-1,8-diene | ≥0.25-<12 |
| EINECS: 227-813-5 | 🚸 Flam. Liq. 3, H226; 🚯 Aquatic Acute 1, | |
| Index number: 601-029-00-7 | H400; Aquatic Chronic 1, H410; 🔶 Skin Irrit. 2, H315; Skin Sens. 1, H317 | |
| CAS: 68424-85-1 | N - Alkyl - N, N - dimethyl - N - | ≥0.1-<0.25 |
| EINECS: 270-325-2 | benzylammoniumchloride | |
| Reg.nr.: 01-2119965180-41 | Skin Corr. 1B, H314; Aquatic Acute 1, H400; Aquatic Chronic 1, H410; Acute Tox. H302 | |
| Regulation (EC) No 648/2004 on a | letergents / Labelling for contents | |
| cationic surfactants, perfumes | | <59 |
| LIMONENE, alpha-Hexylcinnamal | dehvde | |

• Additional information For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

• 4.1 Description of first aid measures

- After inhalation Supply fresh air; consult doctor in case of complaints.
- · After skin contact Rinse with warm water.
- After eye contact Rinse opened eye for several minutes under running water.
- · After swallowing
- Rinse out mouth and then drink plenty of water.
- If symptoms persist consult doctor.
- 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.
- 4.3 Indication of any immediate medical attention and special treatment needed
- No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- · Suitable extinguishing agents
- CO2, powder or water spray. Fight larger fires with water spray or alcohol resistant foam.
- $\cdot \textit{For safety reasons unsuitable extinguishing agents Water with full jet.}$
- \cdot 5.2 Special hazards arising from the substance or mixture
- No further relevant information available.
- · 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

(Contd. on page 4)

GB



(Contd. of page 3)

Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

· Additional information

Collect contaminated fire fighting water separately. It must not enter the sewage system.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Wear protective clothing.
- 6.2 Environmental precautions: Inform respective authorities in case of seepage into water course or sewage system. Dilute with plenty of water. Do not allow to enter sewers/ surface or ground water. Do not allow to penetrate the ground/soil.
- 6.3 Methods and material for containment and cleaning up: Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders). Ensure adequate ventilation.
- 6.4 Reference to other sections
 See Section 7 for information on safe handling
 See Section 8 for information on personal protection equipment.
- See Section 13 for disposal information.

SECTION 7: Handling and storage

- 7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace. Prevent formation of aerosols.
- · Information about fire and explosion protection: No special measures required.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage
- · Requirements to be met by storerooms and receptacles: No special requirements.
- *Information about storage in one common storage facility: Keep away from food, beverages and feed.*
- Further information about storage conditions: Protect from frost.
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

• Additional information about design of technical facilities: No further data; see item 7.

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

67-63-0 propan-2-ol

- WEL Short-term value: 1250 mg/m³, 500 ppm Long-term value: 999 mg/m³, 400 ppm
- · DNELs

67-63-0 propan-2-ol

Oral DNEL 26 mg/kg*d (consumer)

(Contd. on page 5)



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

| Dermal DNEL 888 mg/kg*d (employee) 319 mg/kg*d (consumer) 319 mg/kg*d (consumer) Inhalative DNEL 500 mg/m3 (employee) 88 mg/m3 (consumer) 88 mg/m3 (employee) 88.1 Exposure controls Personal protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gase / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or loe exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation./ the chemical mixture. Not necessary and the chemical mixture. The glove material has to be impermeable and resistant to the product / the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation The sease frough time has to be found out by the manufacturer of the protective gloves and to be observed. • For the permanent contact gloves made of the following materials are suitable: * buty inbber 0.4 mm, 30 min (EN 374) • As protection from splashes gloves made of the following materials are suitable: * buty inbber 0.4 mm, 30 min (EN 374) • Stept protectior | | | | Contd. of pag |
|---|--------------------|----------|---|---------------|
| Inhalative DNEL 500 mg/m3 (employee) 89 mg/m3 (consumer) 8.2 Exposure controls Fersonal protective equipment General protective equipment General protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or loe exposure use self-contained respiratory protective device. Not necessary if room is well-venillated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Selection of the glove material The exore mament contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) Pareterion: Set broker 0,4 mm, 30 min (EN 374) Protection: * intri rubber 0,4 mm, 30 min (EN 374) As protection: * intribuber 0,4 mm, 30 min (EN 374) Protection: Solues recommended during refilling. Setertion | Dermal | DNEL | 888 mg/kg*d (employee) | |
| 89 mg/m3 (consumer) 82 Exposure controls Personal protective equipment General protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gases / funes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or lo exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resists no recommendation to the glove material can be given for the product preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substancer/ preparation Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Work protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * hirtil rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * hirtil rubber 0,4 mm, 30 min (EN 374) Byte protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic Odour threshold: Not determined. PH-value at 20 °C: 4 | | | 319 mg/kg*d (consumer) | |
| 89 mg/m3 (consumer) 8.2 Exposure controls Personal protective equipment General protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection In case of brief exposure or low pollution use respiratory filter device. In case of intensive or lo exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation. The glove material has to be impermeable and resistant to the product / the substancer/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Work Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) Experimention from sylashes gloves made of the following materials are suitable: * butyl rubber 0,4 mm, 30 min (EN 374) Experimention SECTION 9: Physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characceristic Odour threshold: Not determined. pH-value at 20 °C: 4 | Inhalative | DNEL | | |
| 8.2 Exposure controls Personal protective equipment General protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or loe exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation. the chemical mixture. The glove material has to be impermeable and resistant to the product / the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Wor protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * huryl rubber 0.7 mm, 480 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties Otour: Elue Otour: Characteristic | 1 | 21122 | | |
| Personal protective equipment General protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or loe exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation. Felection of the glove material has to be impermeable and resistant to the product/ the substance? preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation www.line of gloves Butyl rubber, BR Penetration time of glove material Protective gloves. Postection from splashes gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties Section: Goggles recommended during refilling. Section: Goggles recommended during refilling. Section: | | | os ing/ins (consumer) | |
| General protective and hygienic measures Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or loexposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substances preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Wwww. Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * butyl rubber 0,4 mm, 30 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: | - | | | |
| Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or loe exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product/ preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation <i>With a construction of glove material on consideration of the penetration times, rates of diffusion and degradation With a construction of glove material on consideration of the penetration times, rates of diffusion and degradation With a construction of glove material on consideration of the penetration times, rates of diffusion and degradation With a construction of glove material on consideration of the penetration times, rates of diffusion and to be observed. Protective gloves. Panetration time of glove material on consideration out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable:</i> * hirti rubber 0 | | | | |
| Do not inhale gases / fumes / aerosols. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or low exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Www Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * hirtil rubber 0,7 mm, 480 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Form: Form: Form: Colour: Characteristic Odour: Characteristic Odour: Characteristic Odour: Characteristic PH-value at 20 *C: | | | | |
| Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or low exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Event Protective gloves. • Adterial of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. • For the permanent contact gloves made of the following materials are suitable: * huiri lubber 0,4 mm, 30 min (EN 374) • As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) • Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties • General Information • Appearance: Form: Fluid Colour: <t< td=""><td></td><td></td><td></td><td></td></t<> | | | | |
| In case of brief exposure or low pollution use respiratory filter device. In case of intensive or lo exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation. Selection of the glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation WWW Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic 0.200*C: 4 | | | | |
| exposure use self-contained respiratory protective device. Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product/ preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Form: Colour: Blue Odour: Characteristic Odour: Characteristic Odour threshold: PH-value at 20°C: 4 | | | | |
| Not necessary if room is well-ventilated. Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product, preparation, the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation <i>WWW WWW</i> Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic Odour: Characteristic Odour: Not determined. <td></td> <td></td> <td></td> <td>sive or lon</td> | | | | sive or lon |
| Protection of hands: * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation. The glove material has to be impermeable and resistant to the product/ the substance/preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * hutyl rubber 0,7 mm, 480 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Odour: Characteristic Odour threshold: PH-value at 20 °C: 4 | | | | |
| * chemical resistant protective gloves (EN 374) Due to missing tests no recommendation to the glove material can be given for the product preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * hutyl rubber 0,7 mm, 480 min (EN 374) As protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic Mot determined. pH-value at 20 °C: 4 | | | | |
| Due to missing tests no recommendation to the glove material can be given for the product preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Form: Form: Form: Form: Form: Characteristic Odour: Odour: Characteristic Odour threshold: PH-value at 20 °C: 4 | | * | | |
| preparation/ the chemical mixture. The glove material has to be impermeable and resistant to the product/ the substance/ preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,7 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic Odour threshold: Not determined. pH-value at 20 °C: 4 | | | | |
| The glove material has to be impermeable and resistant to the product/ the substance/preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Image: Constraint of the glove material on consideration of the penetration times, rates of diffusion and degradation Image: Constraint of the glove material on consideration of the penetration times, rates of diffusion and degradation Image: Constraint of the glove material on consideration of the penetration times, rates of diffusion and degradation Image: Constraint of the glove material of gloves material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * hitril rubber 0,7 mm, 480 min (EN 374) • As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) • Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties • General Information • Appearance: Form: Fluid Colour: Blue Odour Characteristic Odour threshold: Not determined. • pH-value at 20 °C: 4 | | | | product/ |
| preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,7 mm, 480 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties 6.9.1 Information on basic physical and chemical properties 6.9.1 Information Appearance: Form: Form: Form: Colour: Blue Odour: Odour: Odour threshold: PH-value at 20 °C: 4 | | | | |
| Selection of the glove material on consideration of the penetration times, rates of diffusion and degradation Protective gloves. Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Form: Found Colour: Blue Odour: Characteristic Odour threshold: Not determined. pH-value at 20 °C: 4 | The glove | mater | ial has to be impermeable and resistant to the product/ the su | bstance/ |
| degradation | · · | | | |
| Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic Odour threshold: Not determined. pH-value at 20 °C: 4 | | | love material on consideration of the penetration times, rates of diffe | usion and |
| Material of gloves Butyl rubber, BR Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties General Information Appearance: Form: Form: Colour: Blue Odour: Characteristic Not determined. pH-value at 20 °C: 4 | degradatio | п | | |
| The exact break trough time has to be found out by the manufacturer of the protective gloves and to be observed. • For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) • As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) • Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties • General Information on basic physical and chemical properties • General Information • Appearance: Form: Fluid Colour: Blue • Odour: Characteristic • Odour threshold: Not determined. • pH-value at 20 °C: 4 | | | | |
| For the permanent contact gloves made of the following materials are suitable: * butyl rubber 0,7 mm, 480 min (EN 374) As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Characteristic Not determined. pH-value at 20 °C: 4 | The exact <i>b</i> | oreak tr | | loves and l |
| As protection from splashes gloves made of the following materials are suitable: * nitril rubber 0,4 mm, 30 min (EN 374) • Eye protection: Goggles recommended during refilling. • SECTION 9: Physical and chemical properties • 9.1 Information on basic physical and chemical properties • General Information • Appearance: • Form: • Fluid • Colour: • Odour: • Odour: • Odour threshold: • pH-value at 20 °C: 4 | For the per | rmanen | | |
| * nitril rubber 0,4 mm, 30 min (EN 374) • Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties • 9.1 Information on basic physical and chemical properties • General Information • Appearance: Form: Fluid Colour: Blue • Odour: Characteristic • Odour threshold: Not determined. | | | | |
| Eye protection: Goggles recommended during refilling. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: Blue Odour: Odour: Characteristic Not determined. pH-value at 20 °C: | | | | |
| SECTION 9: Physical and chemical properties • 9.1 Information on basic physical and chemical properties • General Information • Appearance: Form: Fluid Colour: Blue • Odour: Characteristic • Odour threshold: Not determined. | | | | |
| • 9.1 Information on basic physical and chemical properties • General Information • Appearance: Form: Fluid Colour: Blue • Odour: Characteristic • Odour threshold: Not determined. • pH-value at 20 °C: 4 | 5-1 | | | |
| · General Information · Appearance: Form: Fluid Colour: Blue · Odour: Characteristic · Odour threshold: Not determined. · pH-value at 20 °C: 4 | SECTIO | N 9: P | hysical and chemical properties | |
| · General Information · Appearance: Form: Fluid Colour: Blue · Odour: Characteristic · Odour threshold: Not determined. · pH-value at 20 °C: 4 | 9 1 Inform | ation o | n hasic physical and chemical properties | |
| • Appearance: Fluid Form: Fluid Colour: Blue • Odour: Characteristic • Odour threshold: Not determined. • pH-value at 20 °C: 4 | | | | |
| Form:FluidColour:BlueOdour:CharacteristicOdour threshold:Not determined.PH-value at 20 °C:4 | | | | |
| • Odour: Characteristic • Odour threshold: Not determined. • pH-value at 20 °C: 4 | 11 | - | Fluid | |
| • Odour threshold: Not determined. • pH-value at 20 °C: 4 | Colour: | | Blue | |
| • Odour threshold:Not determined.• pH-value at 20 °C:4 | Odour: | | Characteristic | |
| - | | shold: | Not determined. | |
| - | | | 1 | |
| (Contd. on pa | nH-value a | ut 20 •C | 4 | |



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

| | (Contd. of pa |
|---|---|
| pH-value 1 %: | 5.0 |
| Change in condition | |
| Melting point/freezing point: | 0 °C |
| Initial boiling point and boiling range | e: 100 °C |
| Flash point: | Not applicable |
| Flammability (solid, gaseous) | Not applicable. |
| Ignition temperature: | not applicable |
| Decomposition temperature: | Not determined. |
| Auto-ignition temperature: | Product is not selfigniting. |
| Explosive properties: | Product does not present an explosion hazard. |
| Explosion limits: | |
| Lower: | Not determined. |
| Upper: | Not determined. |
| Vapour pressure at 20 °C: | 23 hPa |
| Density at 20 °C: | 0.994 g/cm ³ |
| Relative density | Not determined. |
| Vapour density | Not determined. |
| Evaporation rate | Not determined. |
| Solubility in / Miscibility with | |
| Water: | Fully miscible |
| Partition coefficient: n-octanol/water: | Not determined. |
| Viscosity: | |
| dynamic at 20 °C: | 3 mPas |
| kinematic: | Not determined. |
| Solvent content: | |
| Organic solvents: | 2.6 % |
| VOC (EC) | 2.59 % |
| 9.2 Other information | No further relevant information available. |

SECTION 10: Stability and reactivity

• 10.1 Reactivity corresponds to 10.3

· 10.2 Chemical stability

· Thermal decomposition / conditions to be avoided:

No decomposition if used according to specifications.

· 10.3 Possibility of hazardous reactions No dangerous reactions known

• 10.4 Conditions to avoid No further relevant information available.

 \cdot 10.5 Incompatible materials: No further relevant information available.

(Contd. on page 7) GB



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

(Contd. of page 6)

· 10.6 Hazardous decomposition products: No dangerous decomposition products known

| | N 11: Toxicological information |
|---|---|
| | mation on toxicological effects |
| | city Based on available data, the classification criteria are not met. |
| | values relevant for classification: |
| | lecamethylcyclopentasiloxane |
| Dermal | LD50 > 15,000 mg/kg (Rat) |
| | LC50 > 5,000 mg/kg (Rat) |
| | propylene glycol monobutyl ether |
| Oral | LD50 3,300 mg/kg (Rat) |
| 67-63-0 pr | • |
| Dermal | LD50 12,800 mg/kg (can) |
| | 12,800 mg/kg (rabbit) |
| Inhalative | LC50 5,280 mg/kg (Rat) |
| 68424-85 | 1 N-Alkyl-N,N-dimethyl-N-benzylammoniumchloride |
| Oral | LD50 344 mg/kg (Rat) |
| Dermal | LD50 3,340 mg/kg (can) |
| Germ cell Carcinoge Reproduct STOT-sing STOT-report | ets (carcinogenity, mutagenicity and toxicity for reproduction) mutagenicity Based on available data, the classification criteria are not met. nicity Based on available data, the classification criteria are not met. ive toxicity Based on available data, the classification criteria are not met. gle exposure Based on available data, the classification criteria are not met. eated exposure Based on available data, the classification criteria are not met. hazard Based on available data, the classification criteria are not met. |
| SECTIO | - |
| - | propylene glycol monobutyl ether |
| | |
| 67-63-0 pr | 560-1,000 mg/l (fish) |
| - | |
| | 9,640 mg/l (Pimephales promelas) |
| | 13,299 mg/l (Daphnia magna) |
| EC30/72 h | >1,000 mg/l (Desmodesmus subspicatus) |

EC10/18 h >1,000 mg/l (Pseudomonas putida) (DIN 38412)

(Contd. on page 8) GB



Revision: 04.09.2018

Printing date 07.09.2018

Version number 6

Trade name: RM 821

| 68424-85-1 | (Contd. of page 7 N-Alkyl-N,N-dimethyl-N-benzylammoniumchloride | | | |
|--|--|--|--|--|
| | 0.28 mg/l (Pimephales promelas) (US-EPA) | | | |
| | VC50/72 h = 0.03 mg/l (Algae) | | | |
| | 8 h 0.016 mg/l (Daphnia magna) | | | |
| | | | | |
| | 50/96h 0.049 mg/l (Pseudokirchneriella subcapitata) | | | |
| NOEC | 0.032 mg/l (Pimephales promelas) | | | |
| | 0.0042 mg/l (Daphnia magna) | | | |
| 12.3 Bioaco 12.4 Mobili Ecotoxical Remark: Ha Additional COD-value General not The product The surfact as laid dow at the dispo at the dispo at their dire In compliat emulsions. Do not allo sewage syst Harmful to 12.5 Result PBT: Not a | immful to fish ecological information: 2 219000 mg/l does not contain organic complexing agents. ant(s) contained in this preparation complies(comply) with the biodegradability critered in Regulation (EC) No.648/2004 on detergents. Data to support this assertion are hele sal of the competent authorities of the Member States and will be made available to them ct request or at the request of a detergent manufacturer. ace with the prescribed application parameters, the product does not lead to stable w undiluted product or large quantities of it to reach ground water, water course of em. aquatic organisms a of PBT and vPvB assessment | | | |
| · vPvB: | | | | |
| | ecamethylcyclopentasiloxane adverse effects No further relevant information available. | | | |
| | 13: Disposal considerations | | | |
| | treatment methods | | | |
| · Recomment | lation | | | |
| | e disposed together with household garbage. Do not allow product to reach sewag | | | |
| Must not b | e uisposed together with household gurbuge. Do not allow product to reach sewag | | | |
| system. | | | | |
| system. Must be spe | cially treated adhering to official regulations. | | | |
| system. Must be spe | | | | |

- · Uncleaned packaging:
- · Recommendation:

Packaging may be reused or recycled after cleaning.

(Contd. on page 9)

GB



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

Non contaminated packagings may be recycled.

(Contd. of page 8)

· Recommended cleansing agents: Water, if necessary together with cleaning agents.

| SECTION 14: Transport informat | ion |
|--|--|
| · 14.1 UN-Number · ADR, ADN, IMDG, IATA | Void |
| · 14.2 UN proper shipping name · ADR, ADN, IMDG, IATA | Void |
| · 14.3 Transport hazard class(es) | |
| · ADR, ADN, IMDG, IATA · Class | Void |
| · 14.4 Packing group · ADR, IMDG, IATA | Void |
| 14.5 Environmental hazards: Marine pollutant: | No |
| · 14.6 Special precautions for user | Not applicable. |
| · 14.7 Transport in bulk according to Anno Marpol and the IBC Code | e x II of Not applicable. |
| · Transport/Additional information: | Not dangerous according to the above specifications. |
| · UN ''Model Regulation'': | Void |

SECTION 15: Regulatory information

· 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

· Directive 2012/18/EU

- · Named dangerous substances ANNEX I None of the ingredients is listed.
- REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3, 40, 70

· National regulations

· Information about limitation of use:

Employment restrictions concerning juveniles must be observed.

· 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship. A product information sheet can be provided if requested.

(Contd. on page 10)

GB



Printing date 07.09.2018

Version number 6

Revision: 04.09.2018

Trade name: RM 821

| | | (Contd. of page |
|---|---|--|
| · Relevant phrases | | |
| | ble liquid and vapour. | |
| H226 Flammable liqu | | |
| H302 Harmful if swal | | |
| H314 Causes severe | skin burns and eye dame | age. |
| H315 Causes skin irr | itation. | |
| H317 May cause an a | llergic skin reaction. | |
| H319 Causes serious | | |
| H336 May cause drov | vsiness or dizziness. | |
| H400 Very toxic to ac | juatic life. | |
| H410 Very toxic to ad | quatic life with long last | ting effects. |
| Department issuing S | SDS: PCD-D | |
| Contact: | | |
| Department PCD-D | | |
| Tel.: +49-7195-14-25 | 348 | |
| Fax : +49-7195-14-3 | 164 | |
| safetydata@karcher. | com | |
| Abbreviations and ac | ronyms: | |
| ADR: Accord européen s | ur le transport des marchan | ndises dangereuses par Route (European Agreement concerning |
| | Dangerous Goods by Road) | |
| IMDG: International Maria IATA: International Air Tra | time Code for Dangerous Goo | Das |
| | d System of Classification and | d Labelling of Chemicals |
| | ory of Existing Commercial Cl | |
| | Notified Chemical Substances | |
| CAS: Chemical Abstracts S VOC: Volatile Organic Con | ervice (division of the America mounds (USA_EU) | can Chemical Society) |
| DNEL: Derived No-Effect | | |
| LC50: Lethal concentration | | |
| LD50: Lethal dose, 50 perc | | |
| PBT: Persistent, Bioaccum | | |
| vPvB: very Persistent and v Flam. Liq. 2: Flammable li | | |
| Flam. Liq. 3: Flammable li | | |
| Acute Tox. 4: Acute toxicity | | |
| 2 | ion/irritation – Category 1B | |
| Skin Irrit. 2: Skin corrosion | | |
| 5 | mage/eye irritation – Categor | ry 2 |
| Skin Sens. 1: Skin sensitisa | 0 | Contraction 2 |
| 1 0 0 | organ toxicity (single exposures to the aquatic environment | re) – Category 5 - acute aquatic hazard – Category 1 |
| | | - acute aquatic nazara – Category 1 ent - long-term aquatic hazard – Category 1 |
| | | ent - long-term aquatic hazard – Category 3 |
| | the previous version alt | |
| 0.011-776.0 | RM 821/11 | 2.051 |
| 0.011-776.0 | RM 821/11 | 2.051 |